

XTRAFORM 2L

Product Data Sheet

Formable Hardcoated Polycarbonate Film

DESCRIPTION

XtraForm 2L is a formable hardcoated polycarbonate film with a gloss finish on both sides of the film. The print side has a laminate in place to protect the surface prior to processing, but this **must** be removed before printing. This laminate is more transparent than the first (hardcoat) surface laminate, and has higher peel strength.

XtraForm 2L is designed for deep draw 3D film insert molding (FIM) applications using the Xtraform process.



PROCESS RECOMMENDATIONS

Method	Recommendations
Handling	The film must be handled in UV safe conditions at every process stage until the UV cure is complete
Printing	Second surface decoration can be achieved with a variety of suitable screen printing inks, <u>excluding</u> UV inks. Remove the laminate on the print side before printing. The hard coating will slightly retard the drying of solvent inks. The ink manufacturer's process recommendations must be used to develop production processes. We do not recommend that baking cycles, in the printing process, exceed 5 hours at 80 °C. Colour matching of the ink and film must be undertaken with the protective laminates removed ¹
Forming	In a constant smooth action, remove protective laminate on top of the hardcoat surface prior to forming. Use static control measures to prevent contamination. Thermoforming or pressure forming by the Niebling process must be carried out <i>after</i> decoration ¹
Curing	The formed part must be UV cured immediately after forming to prevent any scratching during subsequent processing ¹
Cutting	Trimming of the formed part should be carried out with precision matched metal tooling for optimum results ¹
Inject molding	The printed, formed and trimmed part is inserted into a suitably designed injection mold tool cavity and resin injected onto the printed side of the film ¹

¹Full processing guidelines for printing, cutting, molding, UV curing and forming are available and must be referred to when designing a process using this product



TYPICAL PROPERTIES

Property	XtraForm 2L	Test Method ²
Thickness 180 µm 250 µm 380 µm	180 µm ± 8% 258 µm ± 8% 380 µm ± 8%	Test method 096
Haze	< 1.6%	ASTM D1003
Total Luminous Transmission	89 %	ASTM D1003
Yellowness Index Uncured Cured	≤4 ≤6	ASTM E313
Resistance to Humidity	No adhesion loss or visible change	72 hours @ 60°C,95% RH
Gloss level 20° 60° 85°	85 GU 92 GU 100 GU	ASTM D523 Flat, black back-printed
Atlas ageing Adhesion (% loss) Grey scale	0% 5.0	SAE J2412 225 Kj/m ²
Heat ageing	No adhesion loss or visible change	240 hrs @ 90°C PLAWP 013
Taber abrasion 25 cycles 100 cycles	Change in % haze < 5.0 <15.0	CS10F wheel, 500grams Test method 103

²For details of test method, please contact MacDermid

BASE FILM DATA³

Property	Data	Test Method
Tensile strength	≥ 60 MPa / 23 °C	ASTM D882
Water absorption equilibrium	0.35 %	ASTM D570
Specific gravity	1.2 g/cm ³	ASTM D792
Elongation at break	≥ 100 % / 23 °C	ASTM D882

³Derived from suppliers' literature. The coating slightly enhances most properties.

All properties quoted show typical values Shelf life: 6 months IMDS ID-No: 127637209#2



CONTACT INFORMATION

To confirm this is the most recent issue, please contact us:

AutomotiveFilms@macdermidenthone.com

Americas 245 Freight Street Waterbury, CT 06702, USA (800) 323 0632	Europe & rest of the world Grove Road, Wantage, Oxon OX12 7BZ, UK +44 (0) 1235 771111	Asia 26 Tuas West Road Singapore 638382 +65 6862 3327
---	---	---

Website: industrial.macdermidenthone.com

The information and recommendations in this publication are believed to be accurate and are offered in good faith. Suggestions concerning uses and applications are only the opinion of MacDermid Autotype Limited and/or its affiliates and related entities (referred to herein as "MacDermid") and users should carry out their own testing procedures to confirm suitability for their purposes. Except in case of death or personal injury caused by the materials, MacDermid MAKES NO WARRANTY OF ANY KIND AND EXCLUDES ANY STATUTORY WARRANTY EXPRESS OR IMPLIED other than that materials conform to their current applicable standard specifications. Statements herein therefore should not be construed as guarantees of satisfactory quality or fitness for purpose unless expressly prohibited by compulsory law provisions. The responsibility of MacDermid for claims arising out of breach of guarantee, negligence, strict liability or otherwise is limited to the purchase price of the material.

Suggestions concerning working practices and procedures are based on the practices adopted by existing users of the products and are made in good faith. IT IS THE RESPONSIBILITY OF THE USER TO ENSURE THAT ALL RELEVANT HEALTH AND SAFETY LAWS AND REGULATIONS ARE COMPLIED WITH. MacDermid does not provide any advice on such laws and regulations and accepts no responsibility, express or implied, for breach of such regulations.

WARNING: Nothing in this guide or in these technical specifications should be construed to imply or suggest that the user employ operations or create articles, which would infringe any patents belonging to third parties. It is the customer's responsibility to ensure that its operations, the conditions of processing, and articles of manufacture do not infringe the foregoing patents, or any third-party patents. MacDermid does not accept responsibility for any infringement of intellectual property rights of third parties.